



EPOCOAT 21 N

TECHNICAL DATA SHEET 1/19

PROPERTIES AND RECOMMENDED USAGE

Paint type

EPOCOAT 21 N is polyamide cured two-component glossy epoxy top coat.

Typical and recommended uses

Recommended to use as a top coat in epoxy based systems in environmental classes C2-C5. Can also be coated with polyurethane paints. In kerosene, fuel oil and petrol containers excluding ethanol petrol containers. Fulfills the requirements placed for paint surface inside the kerosene containers by Shell.

Chemical resistance

Used in recommended paint systems and correctly applied withstands splashes and spillage of occasional water, oil and weak process chemicals.

Weather resistance

Epoxy paints have a natural tendency to chalk and discolor on exterior exposure.

TECHNICAL DATA

Volume solids*	50 %
Total mass of solids*	730 g/l
VOC value*	450 g/l

* Values are calculated

Mixing ratio

Resin	3 parts by volume
Cure	1 part by volume

Pot life (+23 °C)

approx. 3 h after mixing

Packaging

	Volume (l)	Size of container (l)
Comp A	12	20
Comp B	4	4

Drying time 60 µm

	+23 °C
Surface dry	1.5 h
To touch	3 h
To recoat (min)	8 h
Fully cured	7 d

Drying times are typical on recommended film thicknesses at given temperatures.

Calculated theoretical coverage and recommended film thickness

Dry	Wet	Coverage
40 µm	80 µm	12.5 m ² /l
60 µm	120 µm	8.3 m ² /l

Practical coverage

Depends on wind conditions, structure to be painted, roughness of the surface and application method.

Colour

White, limited range of RAL-colours

Thinner

OH 17, OH 31 (slow)

Cleaner

OH 17

Finish

Glossy

APPLICATION INSTRUCTIONS

Surface preparations

All solid impurities that could prevent adhesion should be removed from the surfaces to be painted. Remove salts and other water soluble impurities using fresh water with brush, high pressure-, steam- or alkali cleansing. Remove grease and oils by alkali-, emulsion- or solvent cleansing (SFS-en ISO 8504-3, SFS-EN ISO 12944-4). The surfaces should be rinsed carefully with fresh water after cleansing. Old, painted surfaces, in which maximum overcoating interval has expired, additional roughening with suitable method is recommended. The place and time for the surface preparation should be chosen correctly, to avoid contamination and moistening of the treated surface before the paint application.

Primer

EPOCOAT 21 PRIMER

Top coat

EPOCOAT 21 N (Other systems may be specified, depending on area of use.)

Environmental conditions during application

Surface should be dry and clean. During application and drying time the temperature of the paint, air and surface should be above +10 °C and the relative humidity below 80 %. The surface temperature should be min 3 °C above the dew point of the air. Exhaust gases may cause yellowing of the paint during the drying time.

Disclaimer

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, as the paint is often used under conditions beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without notice. Please contact our office for more specific information. The product is intended for professional use only. If there are deviations in the different language versions of the technical data sheets, the English version applies.

Method of application

Use airless spray or brush. Stir resin and cure separately and then mix both components thoroughly. The mixing ratio is 3:1 (resin:cure) by volume. If needed, 0-10 % thinner (OH 17) may be added. High pressure airless spray with a nozzle tip of 0,018"-0,023" orifice. Spray angle depending on the object to be painted. In order to ensure the best possible performance of the product, it is recommended that the paint is at room temperature before the application.

Storage and shelf life

The product must be stored in original sealed containers at temperatures from 5 °C to 30 °C. The storage conditions are to keep the containers in a dry, well ventilated space away from source of heat and ignition. When stored as described above, the unopened component A will keep up to 2 years and unopened component B to 3 years from the date of manufacture. The manufacturing date found in the label is also the batch number of the paint.

Safety

Please follow the environmental and safety instructions displayed on the container and Safety Data Sheet. Use under well ventilated conditions. Do not breathe or inhale mist, use respirator mask. Avoid skin contact. Spillage on the skin should immediately removed with suitable cleanser, soap or water. In case of contact with eyes, rinse immediately with plenty of clean water and if necessary seek medical advice.