

Carbon steel with operating temperature < 120°C

- Structural steel
- Exteriors of equipment, vessels, piping and valves (not insulated)

Typical systems for newbuilding's

Pre-qualifications tested according to Revision 5 of NORSOK M-501 are still valid as the coating systems also fulfil all requirements in Edition 6.

Other options are available – contact TSS

System no.	Surface preparation	Coating system	DFT μm	Test report number
1-85	Sa 2½	Barrier Jotacote Universal, alum. Hardtop CA	90 130 <u>80</u> 300	LAB10-0124-REP, Rev. 1 NORSOK M-501 Revision 5
1-84	Sa 2½	Barrier Jotacote Universal, alum. Hardtop Optima	90 130 <u>80</u> 300	LAB10-0123-REP, Rev. 1 NORSOK M-501 Revision 5
1-109	Sa 2½	Barrier Jotacote Universal, alum. Hardtop Optima	90 130 <u>60</u> 280	3410-09-0023 Mt01 NORSOK M-501 Revision 5
1-102	Sa 2½	Barrier Penguard Express Hardtop XP	75 150 <u>60</u> 285	LAB10-0821-REP NORSOK M-501 Revision 5
1-82	Sa 2½	Barrier Jotamastic Plus Hardtop Optima	75 130 <u>75</u> 280	3410-08-0043 Mt01 NORSOK M-501 Revision 5
1-74	Sa 2½	Barrier Jotamastic 87 Aluminium WG Hardtop XP	75 160 <u>75</u> 310	LAB08-0832-REP NORSOK M-501 Revision 5
1-143	Sa 2½	Barrier Jotamastic 90 WG Hardtop One	60 160 <u>60</u> 280	SL16617 NORSOK M-501 Edition 6
1-133	Sa 2½	Barrier Jotamastic 90 WG Hardtop Pro	60 160 <u>60</u> 280	3400-15-022579 Mt05 NORSOK M-501 Edition 6
1-134	Muki Z 2001 Sweep blast	Barrier Jotamastic 90 WG Hardtop Pro	60 160 <u>60</u> 280	3400-15-022579 Mt06 NORSOK M-501 Edition 6

1-135	Muki Z 2001 Sweep blast	Barrier Jotamastic 90 WG Hardtop Pro	75 130 <u>75</u> 280	3400-15-022579 Mt08 NORSOK M-501 Edition 6
1-136	Sa 2½	Barrier Penguard Universal Hardtop AX	60 160 <u>60</u> 280	3400-15-022579 Mt09, Rev.1 NORSOK M-501 Edition 6
1-129	Sa 2½	Barrier Penguard Universal, alu Hardtop Pro	60 160 <u>60</u> 280	3400-15-019770 Mt02 NORSOK M-501 Edition 6
1-98	Sa 2½	Barrier Plus Jotacote Universal, alum. Hardtop XP	60 160 <u>60</u> 280	3410-10-0049 Mt06 NORSOK M-501 Revision 5
1-107	Sa 2½	Barrier Plus Jotamastic 90 WG, alum. Hardtop CA	60 160 <u>60</u> 280	3410-12-009182 Mt03 NORSOK M-501 Edition 6
1-105	Sa 2½	Barrier Plus Jotamastic 90 WG, alum. Hardtop Optima	60 160 <u>60</u> 280	3410-12-009182 Mt01 NORSOK M501 Edition 6
1-106	Sa 2½	Barrier Plus Jotamastic 90 WG, alum. Hardtop XP	60 160 <u>60</u> 280	3410-12-009182 Mt02 NORSOK M501 Edition 6
1-103	Sa 2½	Barrier Plus Penguard Pro Hardtop Optima	60 150 <u>75</u> 285	SL 12020 NORSOK M-501 Revision 5
1-108	Sa 2½	Barrier Plus Penguard Pro Hardtop XP	60 160 <u>60</u> 280	SL 13342 NORSOK M-501 Edition 6
1-118	Sa 2½	Barrier Plus Penguard Pro Hardtop AX	60 160 <u>60</u> 280	3410-015786 Mt02 NORSOK M-501 Edition 6
1-117	Sa 2½	Barrier Plus Penguard Universal Hardtop AX	60 160 <u>60</u> 280	3410-015786 Mt01 NORSOK M-501 Edition 6
1-144	Sa 2½	Barrier Plus Penguard Universal Hardtop One	60 160 <u>60</u> 280	SL 16618 NORSOK M-501 Edition 6

1-120	Sa 2½	Barrier Plus Penguard Universal Hardtop Optima	60 160 <u>60</u> 280	3410-015786 Mt03 NORSOK M-501 Edition 6
1-128	Sa 2½	Barrier Plus Penguard Universal Hardtop Pro	60 160 <u>60</u> 280	3400-15-019770 Mt01 NORSOK M-501 Edition 6
1-76	Sa 2½	Resist 78 Jotacote Universal, alum. Hardtop XP	60 160 <u>60</u> 280	3410-07-0055 Mt03 NORSOK M-501 Revision 5
1-64	Sa 2½	Resist 78 Jotamastic 87 Aluminium Hardtop XP	60 170 <u>50</u> 280	3410-07-0001 Mt02 NORSOK M-501 Revision 5
1-80	Sa 2½	Resist 86 Jotacote Universal, alum. Hardtop Optima	75 130 <u>75</u> 280	LAB09-0716-REP NORSOK M-501 Revision 5
1-79	Sa 2½	Resist 86 Jotamastic Plus Hardtop Optima	75 130 <u>75</u> 280	LAB09-0715-REP NORSOK M-501 Revision 5
1-130	Sa 2½	Resist 86 Penguard Tie Coat 100 Jotamastic Plus Hardtop Pro	60 30 130 <u>75</u> 295	3400-15-019770 Mt03 NORSOK M-501 Edition 6
1-131	Sa 2½	Resist 86 Penguard Tie Coat 100 Jotamastic 90 WG Hardtop Optima	75 35 150 <u>80</u> 340	3400-15-019770 Mt04 NORSOK M-501 Edition 6
1-90	Sa 2½	Baltoflake Baltoflake	700 <u>700</u> 1400	3410-10-0014 Mt03 NORSOK M-501 Revision 5
1-112	Sa 2½	Muki EPS Baltoflake Baltoflake	25 600 <u>600</u> 1225	SL 13349 NORSOK M-501 Edition 6
1-124	Sa 2½	Baltoflake Baltoflake FC	700 <u>700</u> 1400	3400-14-015786 Mt 11 NORSOK M-501 Edition 6
1-91	Sa 2½	Baltoflake Ecolife Baltoflake Ecolife	700 <u>700</u> 1400	3410-10-0014 Mt04 NORSOK M-501 Revision 5
1-111	Sa 2½	Baltoflake Ecolife Baltoflake Ecolife	600 <u>600</u> 1200	SL 12374 NORSOK M-501 Edition 6

1-113	Sa 2½	Muki EPS Baltoflake Ecolife Baltoflake Ecolife	25 600 <u>600</u> 1225	SL 13350 NORSOK M-501 Edition 6
1-137	Sa 2½	Marathon 1000 GF Marathon 1000 GF Hardtop Pro	500 500 <u>75</u> 1075	3400-15-022579 Mt 10 NORSOK M-501 Edition 6
1-177	Sa 2½	Resist 86 Jotacote Universal HF002 Hardtop XP	60 160 <u>60</u> 280	NORSOK M-501 Edition 6
1-178	Sa 2½	Barrier Jotacote Universal HF002 Hardtop XP	60 160 <u>60</u> 280	NORSOK M-501 Edition 6

- * NORSOK M-501 Edition 6 and switching of topcoats:
 “If agreed by the purchaser, the approved topcoat in a pre-qualified coating system, may substitute another pre-qualified topcoat, provided the intermediate coating is the same and the film-thickness of the topcoats are equal”

Please contact Technical Sales Support department ([+47 33457000](tel:+4733457000) or tss@jotun.com) for further information.

Typical systems for maintenance

Pre-qualifications tested according to Revision 5 of NORSOK M-501 are still valid as the coating systems also fulfil all requirements in Edition 6.

System no.	Surface preparation/ Surface application ¹	Coating system	DFT µm	Test report number
1-142	Sa 2½	Barrier Plus Jotamastic Smart Pack Hardtop One	60 160 <u>60</u> 280	SL 16615
1-161	Sa 2½ UHPWJ-WJ-2	Barrier Smart Pack Jotamastic Smart Pack HB Hardtop One	60 160 <u>60</u> 280	3400-16-024816 Mt06 Rev. B
1-158	≈Sa 2½ Bristle Blaster St 3 80-90 µm	Barrier Smart Pack Jotamastic Smart Pack HB Hardtop One	60 160 <u>60</u> 280	3400-16-024816 Mt03 Rev A
1-157	≈Sa 2½ Grinded St 3 60-75 µm	Barrier Smart Pack Jotamastic Smart Pack HB Hardtop One	60 160 <u>60</u> 280	3400-16-024816 Mt02 Rev B
1-173	Sa 2½ Brush	Barrier Smart Pack Jotamastic Smart Pack HB Hardtop Smart Pack	60 160 <u>60</u> 280	NO17673
1-154	Sa 2½	Barrier Smart Pack Jotamastic Smart Pack HB Hardtop AX	60 160 <u>60</u> 280	3400-17-027222
1-170	Sa 2½ Brush	Jotamastic Smart Pack HB Jotamastic Smart Pack HB Hardtop One	150 150 <u>50</u> 350	3400-17-025417 Mt05
1-125	Sa 2½ St 3	Jotamastic 80, alum. Jotamastic 80, alum. Hardtop XP	100 150 <u>50</u> 300	3410-13-012057 Mt 01
1-168	Sa 2½ Bristle Blaster St 3 80-90 µm Brush	Jotamastic 90 WG, alum. Jotamastic 90 WG Hardtop One	150 150 <u>50</u> 350	3400-17-025417 Mt03

* NORSOK M-501 Edition 6 and switching of topcoats:

“If agreed by the purchaser, the approved topcoat in a pre-qualified coating system, may substitute another pre-qualified topcoat, provided the intermediate coating is the same and the film-thickness of the topcoats are equal”

¹) Unless other application method is specified, airless spraying is the application method used.

2) Other surface preparations are also approved for the same coating system. Available upon request.

Please contact Technical Sales Support department ([+47 33457000](tel:+4733457000) or tss@jotun.com) for further information.