

Walkways, escape routes and lay down areas

Typical systems

Pre-qualifications tested according to Edition 5 of NORSOK M-501 are still valid as the coating systems also fulfil all requirements in Edition 6.

Other options are available- contact TSS

System no.	Surface preparation	Coating system	DFT μm	Test report number
4-1	Sa 2½	Baltoflake Baltoflake Baltoflake – Carborex - Baltoflake	750 750 <u>600</u> 2100	410-02-0013 M13
4-2	Sa 2½	Jotamastic 80, alum. Jotamastic 80, alum. Jota Armour	150 150 <u>1000</u> 1300	3410-10-0014 Mt06
4-3	Sa 2½	Jotamastic 80 WG, alum. Jotamastic 80 WG, alum. Jota Armour WG	150 150 <u>1000</u> 1300	3410-12-006106 Mt01
4-5	Sa 2½	Penguard Universal Marathon 1000 GF + Aggregates Marathon IQ2	200 2300 <u>500</u> 3000	NO 19368
4-6	Sa 2½	Marathon 1000 GF Marathon 1000 GF + Aggregates Marathon IQ2	750 1750 <u>500</u> 3000	NO 19369
4-7	Sa 2½	Marathon 1000 XHB Marathon 1000 XHB + Aggregates Marathon IQ2	750 1750 <u>500</u> 3000	NO 19370
4-9	Sa 2½	Marathon 550 +Aggregate Marathon 550 Hardtop XP	900 500 <u>50</u> 1450	3400-18-029130 Mt01 N4