

NORMAFINE DTM

TECHNICAL DATA SHEET 1/22

PROPERTIES AND RECOMMENDED USAGE

Paint type

NORMAFINE DTM is fast drying, high solid two component, semi-gloss polyurethane coating with an aliphatic isocyanate curing agent. It contains rust preventing pigments. Recommended as a single-coat paint directly to metal or as a topcoat in paint systems.

Typical and recommended uses

NORMAFINE DTM can be used in environmental classes C2 - C3 as a single coat on easily painted steel structures and products such as buildings and equipment. It can also be used as a topcoat in environmental classes C2 - C5 on suitable primers.

Chemical resistance

Used in recommended paint systems, and correctly applied withstands occasional splashes and spillage of water, oil and weak process chemicals.

Weather resistance

Withstands sunlight and UV radiation.

Colour

NCS- and RAL-colours.

The objects painted with the same shade, but using different paint types, might have differences in the appearance and shade due to the variation in the paint properties, gloss levels and application methods.

Finish

Semigloss

TECHNICAL DATA

Volume solids*	65 ± 2 %
Total mass of solids*	1130 g/l
VOC value*	305 g/l

* Values are calculated

Mixing ratio

Resin	9 parts by volume
Cure	1 part by volume

Pot life (+23 °C)

approx. 1 h 20 min after mixing

Packaging

	Volume (l)	Size of container (l)
Comp A	18	20
Comp B	2	2

Drying time 100 µm

	+10 °C	+23 °C	+40 °C
Surface dry	1 h	30 min	15 min
To touch	2 h	1 h	30 min
To recoat	12.5 h	2.5 h	1.5 h
Fully cured	7 d	7 d	3 d

Drying times are typical on recommended film thicknesses at given temperatures.

Calculated theoretical coverage and recommended film thickness

Dry	Wet	Coverage
80 µm	125 µm	8.1 m ² /l
120 µm	185 µm	5.4 m ² /l
160 µm	250 µm	4.0 m ² /l

Practical coverage

Depends on wind conditions, the structure to be painted, the roughness of the surface and the application method.

Thinner

OH 10, OH 66 (slow)

Cleaner

OH 17

APPLICATION INSTRUCTIONS

Surface preparations

All solid impurities that could prevent adhesion should be removed from the surfaces to be painted. Remove salts and other water soluble impurities by wet cleansing with brush, high pressure-, steam- or alkali cleansing. Remove grease and oils by alkali-, emulsion- or solvent cleansing (SFS-EN ISO 8504-3, SFS-EN ISO 12944-4). The surfaces should be rinsed carefully with fresh water after cleansing. Old, painted surfaces, in which maximum overcoating interval has expired, additional roughening with suitable method is recommended. The place and time for the surface preparation should be chosen correctly, to avoid contamination and moistening of the treated surface before the paint application.

Steel surfaces

Blast cleaning to a min. of Sa 2½ (SFS-ISO 8501-1, SFS-EN ISO 8504-2). Cold rolled plates must be roughened with abrasive paper.

Shop primed surfaces

Damaged or corroded surfaces should be blast cleaned to a grade of Sa 2½ (SFS-ISO 8501-2, SFS-EN ISO 12944-4).

Primer

EPOCOAT 21 PRIMER, EPOCOAT 21 HB,
NORECOAT FD PRIMER, NORECOAT HS,
NORMASTIC 405, NORMAZINC SE

Top coat

NORMAFINE DTM

Disclaimer

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, as the paint is often used under conditions beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without notice. Please contact our office for more specific information. The product is intended for professional use only. If there are deviations in the different language versions of the technical data sheets, the English version applies.

Environmental conditions during application

The surface should be dry and clean. During application and drying time the temperature of the paint, air, and surface should be above +10 °C and the relative humidity below 80 %. The surface temperature should be min 3 °C above the dew point of the air.

Method of application

Use an airless spray or brush. Stir the resin and cure separately and then mix both components thoroughly. The mixing ratio is 9 : 1 (resin : cure) by volume. If needed 0 - 10 % thinner (OH 10) may be added. Use a high-pressure airless spray with a nozzle tip of 0.011" - 0.015" orifice. Don't use an adjustable spraying nozzle. The spray angle depends on the object to be painted. In order to ensure the best possible performance of the product, it is recommended that the paint is at room temperature before the application.

Storage and shelf life

The product must be stored in original sealed containers at temperatures from 5 °C to 30 °C. The storage conditions are to keep the containers in a dry, well ventilated space away from source of heat and ignition. When stored as described above, the unopened component A will keep up to 2 years and unopened component B to 1.5 years from the date of manufacture. The date of manufacture is indicated in the label of the paint can as a batch date.

Safety

Please follow the environmental and safety instructions displayed on the container and Safety Data Sheet. Use under well ventilated conditions. Do not breathe or inhale mist, use respirator mask. Avoid skin contact. Spillage on the skin should immediately removed with suitable cleanser, soap or water. In case of contact with eyes, rinse immediately with plenty of clean water and if necessary seek medical advice.