



NORMAALI

ISO 12944-5 PROTECTIVE PAINT SYSTEMS

UPDATED 17.10.2022

In this file you can find Nor-Maali's recommended anti-corrosion paint systems for steel structures.

These ISO 12944-5:2019 protective paint systems have been composed and tested in co-operation by our sales, product development and laboratory staff.

If you need more information about our painting systems, contact sales@nor-maali.fi

Atmospheric corrosivity categories:

- C1 – very low
- C2 – low
- C3 – medium
- C4 – high
- C5 – very high

Categories for water and soil:

- Im1 – immersion in fresh water
- Im2 – immersion in sea or brackish water
- Im3 – buried in soil

Durability:

- Low (L) – Up to 7 years
- Medium (M) – 7 years to 15 years
- High (H) – 15 years to 25 years
- Very high (VH) – more than 25 years

The durability range is not a “guarantee time”. Durability is a technical consideration/planning parameter that can help the owner set up a maintenance programme. A guarantee time is a consideration that is the legal subject of clauses in the administrative part of the contract. The guarantee time is usually shorter than the durability range. There are no rules that link the two periods of time.

Corrosivity category	Examples of typical environments (informative only): Exterior	Examples of typical environments (informative only): Interior
C1 – very low	–	Heated buildings with clean atmospheres, e.g. offices, shops, schools, hotels
C2 – low	Atmospheres with low level of pollution: mostly rural areas	Unheated buildings where condensation can occur, e.g. depots, sports halls
C3 – medium	Urban and industrial atmospheres, moderate sulfur dioxide pollution; coastal areas with low salinity	Production rooms with high humidity and some air pollution, e.g. food-processing plants, laundries, breweries, dairies
C4 – high	Industrial areas and coastal areas with moderate salinity	Chemical plants, swimming pools, coastal ship and boatyards
C5 – very high	Industrial areas with high humidity and aggressive atmosphere and coastal areas with high salinity	Buildings or areas with almost permanent condensation and with high pollution

Category	Environment	Examples of environments and structures
Im1	Fresh water	River installations, hydro-electric power plants
Im2	Sea or brackish water	Immersed structures without cathodic protection (e.g. harbour areas with structures like sluice gates, locks or jetties)
Im3	Soil	Buried tanks, steel piles, steel pipes



CORROSIVITY CATEGORY C2

CARBON STEEL

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C2.01 AK 80/1	Norrapid 7 Norrapid 10	AK	1	80									80	1	●			
C2.01 AK 80/2	Praimex Paja-Pohja	AK	1	40					Norrapid 7 Norrapid 10 Norrapid 12	AK	1	40	80	2	●			
C2.01 AY 80/1	Akvanor 100 SG	AY	1	80									80	1	●			
C2.02 AK 100/1	Norrapid 7 Norrapid 10	AK	1	100									100	1	●	●		
C2.02 AK 100/2	Praimex Paja-Pohja	AK	1	60					Norrapid 7 Norrapid 10 Norrapid 12	AK	1	40	100	2	●	●		
C2.02 AY 100/1	Akvanor 100 SG	AY	1	100									100	1	●	●		
C2.03 AK 160/2	Praimex Paja-Pohja	AK	1	80					Norrapid 7 Norrapid 10 Norrapid 12	AK	1	80	160	2	●	●	●	
C2.04 AK 200/3	Praimex Paja-Pohja	AK	1	80	Praimex Paja-Pohja	AK	1	80	Norrapid 7 Norrapid 10 Norrapid 12	AK	1	40	200	3 (2-3)	●	●	●	●
C2.05 AY 120/1	Akvanor 100 SG	AY	1	120									120	1	●	●	●	
C2.05 EP 120/1	Epotex HB Noreguard HS Norepox HS Norepox Aqua DTM	EP	1	120									120	1	●	●	●	
C2.05 EP 120/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NOR E-Primer	EP	1	60					Epocoat 210 Epocoat 21 N Epotex HB Norepox HS Norepox Aqua DTM	EP	1	60	120	2	●	●	●	
C2.05 EPPUR 120/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NOR E-Primer	EP	1	60					Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	60	120	2	●	●	●	

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C2.05 EPPUR 120/2	NOR E-Primer	EP	1	60					NoreFast HS	PUR	1	60	120	2	●	●	●	
C2.05 PUR 120/1	Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	120									120	1	●	●	●	
C2.06 EP 180/2	NorECOat FD Primer	EP	1	100					Norepox Aqua DTM	EP	1	80	180	2	●	●	●	●
C2.06 EPPUR 180/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer	EP	1	100					Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	80	180	2	●	●	●	●
C2.06 EPPUR 180/2	NorECOat FD Primer	EP	1	120					NoreFast HS	PUR	1	60	180	2	●	●	●	●
C2.06 EPPUR 180/2	Norepox Aqua DTM	EP	1	100					Normadur Aqua DTM	PUR	1	80	180	2	●	●	●	●
C2.07 EPZn(R) 60/1	Normazinc SE Normazinc Plus	Zn(R)	1	60									60	1	●	●	●	
C2.08 EPZn(R)EP 160/2	Normazinc SE Normazinc Plus	Zn(R)	1	60					Epotex HB Noreguard HS Norepox HS Norepox Aqua DTM	EP	1	100	160	2	●	●	●	●
C2.08 EPZn(R)PUR 160/2	Normazinc SE Normazinc Plus	Zn(R)	1	60					Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	100	160	2	●	●	●	●

The background features a stack of several metal plates, likely carbon steel, with a prominent blue overlay on the left side. The surface of the plates is covered with numerous small, glistening water droplets, suggesting a humid or wet environment. The lighting is soft, highlighting the texture of the metal and the individual droplets.

CORROSIVITY CATEGORY C3

CARBON STEEL

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C3.01 AK 100/2	Praimex Paja-Pohja	AK	1	60					Norrapid 7 Norrapid 10 Norrapid 12	AK	1	40	100	2 (1-2)	●			
C3.02 AK 160/2	Praimex Paja-Pohja	AK	1	80					Norrapid 7 Norrapid 10 Norrapid 12	AK	1	80	160	2	●	●		
C3.03 AK 200/3	Praimex Paja-Pohja	AK	1	80	Praimex Paja-Pohja	AK	1	80	Norrapid 7 Norrapid 10 Norrapid 12	AK	1	40	200	3 (2-3)	●	●	●	
C3.04 AK 260/3	Praimex Paja-Pohja	AK	1	90	Praimex Paja-Pohja	AK	1	90	Norrapid 7 Norrapid 10	AK	1	80	260	3 (2-4)	●	●	●	●
C3.05 AY 120/1	Akvanor 100 SG	AY	1	120									120	1	●	●		
C3.05 EP 120/1	Epotex HB Noreguard HS Norepox HS Normastic 405 Norepox Aqua DTM	EP	1	120									120	1	●	●		
C3.05 EP 120/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NOR E-Primer	EP	1	60					Epocoat 210 Epocoat 21 N Epotex HB Norepox HS Norepox Aqua DTM	EP	1	60	120	2	●	●		
C3.05 EPPUR 120/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NOR E-Primer	EP	1	60					Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	60	120	2	●	●		
C3.05 EPPUR 120/2	NOR E-Primer	EP	1	60					NoreFast HS	PUR	1	60	120	2	●	●		
C3.05 PUR 120/1	Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	120									120	1	●	●		

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C3.06 EP 180/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer Normastic 405	EP	1	100					Epocoat 210 Epocoat 21 N Epotex HB Noreguard HS Norepox HS	EP	1	80	180	2	●	●	●	
C3.06 EP 180/2	NorECOat FD Primer	EP	1	100					Norepox Aqua DTM	EP	1	80	180	2	●	●	●	
C3.06 EPPUR 180/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer	EP	1	100					Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	80	180	2	●	●	●	
C3.06 EPPUR 180/2	NorECOat FD Primer	EP	1	120					NoreFast HS	PUR	1	60	180	2	●	●	●	
C3.06 EPPUR 180/2	Norepox Aqua DTM	EP	1	100					Normadur Aqua DTM	PUR	1	80	180	2	●	●	●	
C3.07 EP 240/2	Norepox Aqua DTM	EP	1	120					Norepox Aqua DTM	EP	1	120	240	2	●	●	●	●
C3.07 EPPUR 240/2	NorECOat FD MIO Primer Normastic 405 AL Normastic 405 Harm. / Pun.	EP	1	140					Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	100	240	2 (2-3)	●	●	●	●
C3.07 EPPUR 240/2	NorECOat FD MIO Primer	EP	1	140					Normadur Aqua DTM	PUR	1	100	240	2	●	●	●	●

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C3.08 EPZn(R) 60/1	Normazinc SE Normazinc Plus	Zn(R)	1	60									60	1	●	●		
C3.09 EPZn(R)EP 160/2	Normazinc SE Normazinc Plus	Zn(R)	1	60					Epotex HB Noreguard HS Norepox HS Norepox Aqua DTM	EP	1	100	160	2	●	●	●	
C3.09 EPZn(R)PUR 160/2	Normazinc SE Normazinc Plus	Zn(R)	1	60					Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	100	160	2	●	●	●	
C3.10 EPZn(R)EP 200/3	Normazinc SE Normazinc Plus	Zn(R)	1	60	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer NOR E-Primer	EP	1	80	Epocoat 210 Epocoat 21 N Epotex HB Norepox HS Norepox Aqua DTM	EP	1	60	200	3	●	●	●	●
C3.10 EPZn(R)EPPUR 200/3	Normazinc SE Normazinc Plus	Zn(R)	1	60	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer NOR E-Primer	EP	1	80	Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	60	200	3	●	●	●	●
C3.10 EPZn(R)PUR 200/2	Normazinc SE Normazinc Plus	Zn(R)	1	60					Normafine 80	PUR	1	140	200	2	●	●	●	●



CORROSIVITY CATEGORY C4

CARBON STEEL

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C4.01 AK 160/2	Praimex Paja-Pohja	AK	1	80					Norrapid 7 Norrapid 10 Norrapid 12	AK	1	80	160	2	●			
C4.02 AK 200/3	Praimex Paja-Pohja	AK	1	80	Praimex Paja-Pohja	AK	1	80	Norrapid 7 Norrapid 10 Norrapid 12	AK	1	40	200	3 (2-3)	●	●		
C4.03 AK 260/3	Praimex Paja-Pohja	AK	1	90	Praimex Paja-Pohja	AK	1	90	Norrapid 7 Norrapid 10 Norrapid 12	AK	1	80	260	3 (2-4)	●	●	●	
C4.04 EP 120/1	Epotex HB Noreguard HS Norepox HS Normastic 405 Norepox Aqua DTM	EP	1	120									120	1	●			
C4.04 EP 120/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NOR E-Primer	EP	1	60					Epocoat 210 Epocoat 21 N Epotex HB Norepox HS Norepox Aqua DTM	EP	1	60	120	2	●			
C4.04 EPPUR 120/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NOR E-Primer	EP	1	60					Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	60	120	2	●			
C4.04 EPPUR 120/2	NOR E-Primer	EP	1	60					NoreFast HS	PUR	1	60	120	2	●			
C4.04 PUR 120/1	Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	120									120	1	●			

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C4.05 EP 180/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer Normastic 405	EP	1	100					Epocoat 210 Epocoat 21 N Epotex HB Noreguard HS Norepox HS	EP	1	80	180	2	●	●		
C4.05 EP 180/2	NorECOat FD Primer	EP	1	100					Norepox Aqua DTM	EP	1	80	180	2	●	●		
C4.05 EPPUR 180/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer	EP	1	100					Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	80	180	2	●	●		
C4.05 EPPUR 180/2	NorECOat FD Primer	EP	1	120					NoreFast HS	PUR	1	60	180	2	●	●		
C4.05 EPPUR 180/2	Norepox Aqua DTM	EP	1	100					Normadur Aqua DTM	PUR	1	80	180	2	●	●		
C4.06 EP 240/2	Norepox Aqua DTM	EP	1	120					Norepox Aqua DTM	EP	1	120	240	2	●	●	●	
C4.06 EP 240/3	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer Nor E-Primer	EP	1	80	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer Nor E-Primer	EP	1	80	Epocoat 210 Epocoat 21 N Epotex HB Noreguard HS Norepox HS Norepox Aqua DTM	EP	1	80	240	3 (2-3)	●	●	●	
C4.06 EPPUR 240/2	NorECOat FD MIO Primer	EP	1	140					Normadur Aqua DTM	PUR	1	100	240	2	●	●	●	
C4.06 EPPUR 240/3	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer Nor E-Primer	EP	1	80	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer Nor E-Primer	EP	1	80	Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	80	240	3 (2-3)	●	●	●	

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C4.07 EP 300/3	NorECOat FD MIO Primer Normastic 405 AL Normastic 405 Harm./ Pun.	EP	1	120	NorECOat FD MIO Primer Normastic 405 AL Normastic 405 Harm./ Pun.	EP	1	120	Epocoat 210 Epocoat 21 N Epotex HB Norepox HS	EP	1	60	300	3 (2-4)	●	●	●	●
C4.07 EPPUR 300/2	NorECOat HS Primer	EP	1	240					NoreFast HS	PUR	1	60	300	2	●	●	●	●
C4.07 EPPUR 300/3	NorECOat FD MIO Primer Normastic 405 AL Normastic 405 Harm./ Pun.	EP	1	120	NorECOat FD MIO Primer Normastic 405 AL Normastic 405 Harm./ Pun.	EP	1	120	Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	60	300	3	●	●	●	●
C4.08 EPZn(R) 60/1	Normazinc SE Normazinc Plus	Zn(R)	1	60									60	1	●			
C4.09 EPZn(R)EP 160/2	Normazinc SE Normazinc Plus	Zn(R)	1	60					Epotex HB Noreguard HS Norepox HS Norepox Aqua DTM	EP	1	100	160	2	●	●		
C4.09 EPZn(R)PUR 160/2	Normazinc SE Normazinc Plus	Zn(R)	1	60					Normadur 65 Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	100	160	2	●	●		

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C4.10 EPZn(R)EP 200/3	Normazinc SE Normazinc Plus	Zn(R)	1	60	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer Nor E-Primer	EP	1	80	Epocoat 210 Epocoat 21 N Epotex HB Norepox HS Norepox Aqua DTM	EP	1	60	200	3	●	●	●	
C4.10 EPZn(R)EPPUR 200/3	Normazinc SE Normazinc Plus	Zn(R)	1	60	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer Nor E-Primer	EP	1	80	Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	60	200	3	●	●	●	
C4.10 EPZn(R)PUR 200/2	Normazinc SE Normazinc Plus	Zn(R)	1	60					Normafine 80	PUR	1	140	200	2	●	●	●	
C4.11 EPZn(R)EP 260/3	Normazinc Plus	Zn(R)	1	60	NorECOat FD Primer NorECOat HS Primer Normastic 405	EP	1	140	Epocoat 210 Epocoat 21 N Epotex HB Norepox HS Norepox Aqua DTM	EP	1	60	260	3 (3-4)	●	●	●	●
C4.11 EPZn(R)EPPUR 260/3	Normazinc Plus	Zn(R)	1	60	NorECOat FD Primer NorECOat HS Primer Normastic 405	EP	1	140	Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	60	260	3 (3-4)	●	●	●	●



CORROSIVITY CATEGORY C5

CARBON STEEL

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C5.01 EP 180/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer Normastic 405	EP	1	100					Epocoat 210 Epocoat 21 N Epotex HB Noreguard HS Norepox HS	EP	1	80	180	2	●			
C5.01 EP 180/2	NorECOat FD Primer	EP	1	100					Norepox Aqua DTM	EP	1	80	180	2	●			
C5.01 EPPUR180/2	Epocoat 21 HB NorECOat FD Primer NorECOat HS Primer Normastic 405	EP	1	120					Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	60	180	2	●			
C5.01 EPPUR180/2	NorECOat FD Primer	EP	1	120					NoreFast HS	PUR	1	60	180	2	●			
C5.02 EP 240/2	Norepox Aqua DTM	EP	1	120					Norepox Aqua DTM	EP	1	120	240	2	●	●		
C5.02 EP 240/3	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer	EP	1	80	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer	EP	1	80	Epocoat 210 Epocoat 21 N Epotex HB Noreguard HS Norepox HS	EP	1	80	240	3 (2-3)	●	●		
C5.02 EPPUR 240/2	NorECOat FD MIO Primer	EP	1	140					Normadur Aqua DTM	PUR	1	100	240	2	●	●		
C5.02 EPPUR 240/3	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer	EP	1	80	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer	EP	1	80	Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	80	240	3 (2-3)	●	●		

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C5.03 EP 300/3	Epocoat 21 HB NorECOat FD MIO Primer NorECOat HS Primer	EP	1	120	Epocoat 21 HB NorECOat FD Primer NorECOat HS Primer	EP	1	120	Epocoat 210 Epocoat 21 N Epotex HB Norepox HS	EP	1	60	300	3 (2-4)	●	●	●	
C5.03 EPPUR 300/2	NorECOat HS Primer	EP	1	240					NoreFast HS	PUR	1	60	300	2	●	●	●	
C5.03 EPPUR 300/3	Epocoat 21 HB NorECOat FD Primer NorECOat HS Primer	EP	1	120	Epocoat 21 HB NorECOat FD Primer NorECOat HS Primer	EP	1	120	Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	60	300	3 (2-4)	●	●	●	
C5.04 EPPUR 360/3	NorECOat FD MIO Primer Normastic 405 AL Normastic 405 <i>Harm. / Pun.</i>	EP	1	140	NorECOat FD MIO Primer Normastic 405 AL Normastic 405 <i>Harm. / Pun.</i>	EP	1	140	Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	80	360	3	●	●	●	●
C5.05 EPZn(R)EP 160/2	Normazinc SE Normazinc Plus	Zn(R)	1	60					Epotex HB Noreguard HS Norepox HS	EP	1	100	160	2	●			
C5.05 EPZn(R)PUR 160/2	Normazinc SE Normazinc Plus	Zn(R)	1	60					Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	100	160	2	●			

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
C5.06 EPZn(R)EP 200/3	Normazinc SE Normazinc Plus	Zn(R)	1	60	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer	EP	1	80	Epocoat 210 Epocoat 21 N Epotex HB Norepox HS	EP	1	60	200	3	●	●		
C5.06 EPZn(R)EPPUR 200/3	Normazinc SE Normazinc Plus	Zn(R)	1	60	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer NorECOat HS Primer	EP	1	80	Normadur 65 HS Normadur 50 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS Normadur Aqua DTM	PUR	1	60	200	3	●	●		
C5.06 EPZn(R)PUR 200/2	Normazinc SE Normazinc Plus	Zn(R)	1	60					Normafine 80	PUR	1	140	200	2	●	●		
C5.07 EPZn(R)EP 260/3	Normazinc Plus	Zn(R)	1	60	NorECOat FD MIO Primer	EP	1	120	Epocoat 210 Epocoat 21 N Epotex HB Noreguard HS Norepox HS	EP	1	80	260	3-4	●	●	●	
C5.07 EPZn(R)EPPUR 260/3	Normazinc Plus	Zn(R)	1	60	NorECOat FD MIO Primer	EP	1	120	Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	80	260	3-4	●	●	●	
C5.08 EPZn(R)EP 320/3	Normazinc Plus	Zn(R)	1	60	Normastic 405	EP	1	200	Epocoat 210 Epocoat 21 N Epotex HB Norepox HS	EP	1	60	320	3-4	●	●	●	●
C5.08 EPZn(R)EPPUR 320/3	Normazinc Plus	Zn(R)	1	60	Normastic 405	EP	1	200	Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	60	320	3-4	●	●	●	●



CORROSIVITY CATEGORIES C2-C5

HOT DIP GALVANIZED STEEL

Our recommendations for hot dip galvanized steel systems:

*Preparation grade: SaS

*Priming coat: Mist coat with high thinned epoxy primer

System No.	Corrosivity category	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY				
		Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high	
G2.01 EP/PUR 80/1	C2	Epotex HB Normafine 50 TC	EP PUR	1	80									80	1	●	●	●		
G2.02		N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	●	●	●	●
G2.03 EP 120/1		Epotex HB	EP	1	120										120	1 (1-2)	●	●	●	●
G3.01 EP/PUR 80/1	C3	Epotex HB Normafine 50 TC	EP PUR	1	80									80	1	●	●			
G3.02 EP 120/1		Epotex HB	EP	1	120										120	1	●	●	●	
G3.03		N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	●	●	●	
G3.04 EPPUR 160/2		Epocoat 21 Primer	EP	1	80					Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	80	160	2	●	●	●	●	
G3.05		N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	●	●	●	●
G4.01 EP 80/1		C4	Epotex HB	EP	1	80									80	1	●			
G4.02 EP 120/1	Epotex HB		EP	1	120										120	1 (1-2)	●	●		
G4.03	N/A		N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	●	●		
G4.04 EP 160/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer Nor E-Primer		EP	1	80					Epocoat 210 Epocoat 21 N Epotex HB Noreguard HS Norepox HS	EP	1	80	160	2	●	●	●		
G4.05	N/A		N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	●	●	●	
G4.06 EPPUR 200/2	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer		EP	1	100					Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	100	200	2 (2-3)	●	●	●	●	

Our recommendations for hot dip galvanized steel systems:

*Preparation grade: SaS

*Priming coat: Mist coat with high thinned epoxy primer

System No.	Corrosivity category	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
		Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
G5.01 EPPUR 120/2	C5	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer	EP	1	60					Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	60	120	2	●			
G5.02a		N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	●			
G5.02b EPPUR 160/2		Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer	EP	1	80					Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	80	160	2	●	●		
G5.03		N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	●	●		
G5.04 EPPUR 200/3		Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer	EP	1	60	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer	EP	1	60	Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	80	200	3 (2-3)	●	●	●	
G5.05 EPPUR 240/3		Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer	EP	1	80	Epocoat 21 HB Epocoat 21 Primer NorECOat FD Primer	EP	1	80	Normadur 50 HS Normadur 65 HS Normafine 20 Normafine 40 HS Normafine 80 Normafine HS	PUR	1	80	240	3	●	●	●	●



CATEGORIES FOR WATER AND SOIL

CARBON STEEL

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
I.01 EPZn(R)EP 360/3	Normazinc Plus	Zn(R)	1	60	Normastic 405	EP	1	150	Normastic 405	EP	1	150	360	3 (2-4)	●	●	●	
I.02 EPZn(R)EP 500/3	Normazinc Plus	Zn(R)	1	60	Normastic 405	EP	1	220	Normastic 405	EP	1	220	500	3 (2-5)	●	●	●	●
I.03 EP 380/2	Normastic 405 AL	EP	1	190					Normastic 405	EP	1	190	380	2 (2-4)	●	●	●	
I.04 EP 540/2	Epocoat 280 GF	EP	1	270					Epocoat 280 GF	EP	1	270	540	2 (2-4)	●	●	●	●
I.05 EP 400/2	Normastic 405 AL	EP	1	200					Normastic 405	EP	1	200	400	2 (1-3)	●	●	●	
I.06 EP 600/2	Epocoat 280 GF	EP	1	300					Epocoat 280 GF	EP	1	300	600	2 (2-3)	●	●	●	●

Im1, Im2 – TESTED ACCORDING TO ISO 12944-6:2018

System No.	PRIMER COAT				INTERMEDIATE COAT				TOPCOAT				SYSTEM		DURABILITY			
	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	Product name	Product type	Coats	DFT (µm)	DFT (µm) total	Total coats	low	med	high	very high
Im1 HIGH EP 400/2	NorECOat HS Primer	EP	1	200					NorECOat HS Primer	EP	1	200	400	2	●	●	●	
Im1 VERY HIGH EP 600/3	NorECOat HS Primer	EP	1	200	NorECOat HS Primer	EP	1	200	NorECOat HS Primer	EP	1	200	600	3	●	●	●	●
Im2 HIGH EP 500/2	NorECOat HS Primer	EP	1	250					NorECOat HS Primer	EP	1	250	500	2	●	●	●	
Im2 VERY HIGH EP 600/3	NorECOat HS Primer	EP	1	200	NorECOat HS Primer	EP	1	200	NorECOat HS Primer	EP	1	200	600	3	●	●	●	●



**WE MAKE
IT TO LAST.
WE MAKE
IT FAST.**

NOR MAALI

COMMITTED TO COATING.